

FLEX Classic Gloss

Technical Data Sheet



11 Bennet Avenue,
Melrose Park, SA 5039
Phone: (08) 8357 5444
info@dtktextiles.com.au
www.dtktextiles.com.au

FLEX CLASSIC GLOSS

has a glossy coating giving your logos a shiny gloss finish. The Gloss finish is ideal to decorate garments with a creative Retro vibe or you can just give your T-Shirts a unique look.

Suitable for LAYERING.

Composition	PU/Copes
Thickness	100 Microns
Carrier	Polyester
Finish	Glossy
Fabrics	Cotton, Polyester and Blended Fabrics


CUTTER SPECIFICATIONS (GUIDELINES ONLY)

Blade	Standard 45°
Offset	
Mimaki 0.300	Roland 0.250
Blade Pressure	
Mimaki 70/90g (Protrusion 0.75mm)	Roland 90/100g
Minimum Text Size Of Cut	7mm

TECHNICAL INFORMATION



CUT



APPLICATION



AVAILABILITY



WASHING - 24HRS AFTER APPLICATION



APP TAPE

NOT REQUIRED

Application Instructions

1 CUT

EQUIPMENT/MATERIALS: Cutter

- If using a printer/cutter, ensure to set heaters to OFF.
- Feed vinyl into the cutter with the glue side facing upwards.
- Cut the design in 'mirror/reverse' on the glue side.
- Perform test cuts to ensure proper blade depth when cutting.
- Do not cut through the backing.
- 45° Blade for cutting is preferred for optimum result.
- The backing carrier should only be lightly scored when cutting.

2 WEED

EQUIPMENT/MATERIALS: Weeding tool.

- Weed away excess vinyl, i.e. anything that is not going to be applied to the garment.
- Only the desired vinyl should be left on backing sheet, ready for application.

3 PRESS

EQUIPMENT/MATERIALS: Heat press

- Pre Press Garment for 2-3 Seconds.
- Place transfer on garment in desired position, and heat press according to application guidelines.
- Once pressed, peel away clear carrier from the transfer (as per application guidelines).
- For best results and increased washability: After removing the backing, cover transfer with sheet of silicon/teflon or baking paper and perform a second press for 3-5 seconds.

APPLICATION NOTE:

Guidelines are provided as a recommendation only. They will vary depending on the machine, fabric and environmental conditions.

